

TRANSLATION (VERIFICATION)

RE: U.S. PATENT APPLICATION SERIAL NO.: 10/789,504

I, Scott Lin of Lee and Li Attorneys-at-Law (7F, 201, Tun Hua N. Road, Taipei 105, Taiwan, ROC 10508), hereby declare that I am conversant with Chinese and English languages and that I am the translator of the document(s) attached and certify that to the best of my knowledge and belief that the following is a true and correct translation of the priority document, ROC (Taiwan) Patent Application No.: 092104467 entitled "MATERIAL COMPOSITION FOR PACKAGING PHOTO-SENSITIVE ELEMENTS AND METHOD OF USING THE SAME."

Dated this 1 December 2008

Scott Lin 2008/12/1

**English Translation of Priority Document of U.S. PATENT
APPLICATION SERIAL NO.: 10/789,504**

**Title of the invention: MATERIAL COMPOSITION FOR
PACKAGING OF LIGHT-SENSITIVE COMPONENTS AND
METHOD OF USING THE SAME**

Abstract of the Disclosure

The invention pertains to a material composition for packaging. The composition comprises (a) an epoxy resin and (b) a curing agent, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.7 to 1.1. The invention also pertains to a method of using said material composition for packaging a light-sensitive component on a substrate.

Background of the Invention

Field of the Invention

[0001] The present invention relates to a material composition and its use for the packaging of light-sensitive components.

Description of the Prior Art

[0002] In view of the coming of digital age, light-sensitive components have been widely utilized in various electronic products. Particularly, the development of image sensors has progressed rapidly.

[0003] In general, a method for packaging an image sensor comprises using a mold compound to form a dam around each modular circuit by a transfer molding process; fixing an image sensor to the circuit by a conductive adhesive and accomplishing the wire bonding; applying an adhesive over the dam and placing a glass sheet on the adhesive; and curing the adhesive. ROC Patent Publications No. 459355, 478136, 503574, and 501244 have disclosed packaging structures and methods of image sensors.

[0004] In conventional processes, the light-transmission layer covering image sensor chips is normally glass, as disclosed in the above-mentioned patent publications. This is because glass has low refractive indices, high light-transmission, and scratch resistance. However, in the processes utilizing light-transmission layers of glass, the chips can only be packaged one by one. Such packaging manner will consume a larger amount of efforts and time, cannot achieve good yields,

and is costly.

[0005] ROC Patent Publication No. 489532 describes a stacked structure of an image sensor. This patent publication also discloses utilizing a molding compound and transfer molding, but the light-transmission layer for covering by molding is a transparent resin layer rather than a glass sheet. Nonetheless, said patent publication does not teach, disclose, or suggest what the properties which the resin would possess are or what the effects which the resin would have on light are.

[0006] Although conventional epoxy resins with a benzene ring, such as bisphenol A epoxy resin, bisphenol F epoxy resin, and nathalene-type epoxy resin, are transparent, the refractive indices of such resins upon curing are all higher than 1.50. This is because when the visible light passes through a benzene ring, the unsaturated π bond of the benzene ring will absorb the light to reduce a $\pi - \pi^*$ interaction and to alter the refractive indices and the light transmission rates. The use of those epoxy resins without any benzene rings may effectively reduce refractive indices. However, such resins do not have the properties, such as high glass transition temperatures and heat resistance, that glass possesses.

[0007] The inventors of the subject application have found that there are certain material compositions that are useful as encapsulating materials for packaging, in particular, the packaging of image sensors. Such material compositions, after being cured, will provide the advantages of high glass transition temperatures, low refractive indices, high light transmission, and scratch resistance, and can be used in transparent layers and as substitutes for glass. When utilizing the compositions of the

present invention for packaging on a substrate, said compositions may be cured by heat and then the packaged substrate can be divided into single modules. Such packaging manner is simpler than that for single chip when using glass, and will reduce production cost and enhance production capacity and yield.

Summary of the Invention

[0008] One of the objects of the invention is to provide a material composition for packaging comprising (a) an epoxy resin and (b) a curing agent, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.7 to 1.1.

[0009] One more object of the present invention is to provide a method of using the above packaging material composition for packaging light-sensitive components on a substrate.

Detailed Description of the Invention

[0010] The material composition for packaging of the present invention comprises (a) an epoxy resin and (b) a curing agent wherein the mixing ratio by weight of said epoxy resin to said curing agent is in the range of from 0.7 to 1.1, preferably from 0.85 to 1.0.

[0011] There are no special requirements for the epoxy resins which can be used in the present invention. Examples of useful epoxy resins include bisphenol A epoxy resin, bisphenol F epoxy resin, an aliphatic epoxy resin, and a cycloaliphatic epoxy resin and a mixture thereof, of which the aliphatic epoxy resin and cycloaliphatic epoxy resin are the preferred epoxy resin. Non-limiting examples of suitable epoxy resins

include, for example, ERL-4221 and ERL-4229, commercially available from Dow Chemical; EPON 1510, Holxy Modifier 7, Holxy Modifier 8, Holxy Modifier 61, Holxy Modifier 116, Holxy Modifier 48, Holxy Modifier 67, Holxy Modifier 68, and Holxy Modifier 107, commercially available from Resolution; and EPICLON EXA-7015, EXA-7120, and EPICLON 726D, commercially available from Dainippon Ink & Chemical, Inc.

[0012] The curing agents which may be useful in the present invention are obvious to persons skilled in the art. Non-limiting examples of the curing agents include, for example, acid anhydrides. Examples of useful acid anhydrides include hexahydrophthalic anhydride, methyl hexahydrophthalic anhydride ("MHHPA"), methyl-bicyclo[2,2,1]-heptene-2,3-dicarboxylic anhydride (abbreviated as "NMA"; Nadic Methyl Anhydride), succinic anhydride, and hexafluoroisopropylidene-2,2-bisphthalic anhydride, and a mixture thereof.

[0013] The material composition for packaging of the present invention may optionally comprise one or more additives well known to persons skilled in the art. Such additives include, for example, a promoter, an antifoaming agent, and an antioxidant.

[0014] The promoters which may be useful in the present invention are well known to persons skilled in the art. Non-limiting examples of the useful promoters include the quaternary ammonium salts, imidazole compounds, and salts of 1,8-diazabicyclo[5,4,0]-undec-7-ene ("DBU") and a mixture thereof. The quaternary ammonium salts useful as promoters are well known to persons skilled in the art. Non-limiting examples of such quaternary ammonium salts include benzyl tributyl ammonium

halides, benzyl trimethyl ammonium halides, benzyl tripropyl ammonium halides, phenyl tributyl ammonium halides, tetrabutyl ammonium halides, triphenyl benzyl ammonium halides, tetraethyl ammonium halides, and hexadecyl trimethyl ammonium halides.

[0015] The present invention also pertains to a method of using the above material composition in packaging light-sensitive components, comprising applying the material composition to the light-sensitive components on a substrate. According to the present invention, the light-sensitive components include, but are not limited to, image sensors. Non-limiting examples of the substrates include printed circuit boards and lead frames.

[0016] According to one embodiment of the present invention, the material composition for packaging image sensors comprises (a) an epoxy resin selected from the group consisting of an aliphatic epoxy resin, a cycloaliphatic epoxy resin, and a mixture thereof and (b) a curing agent selected from the group consisting of acid anhydrides, wherein the mixing ratios of said epoxy resin to said curing agent are in the range of from 0.7 to 1.1, preferably 0.85 to 1.0.

[0017] The present invention will be further described in the following examples. However, the examples will not make any limitations to the scope of the invention. Any modifications or alterations on the invention that can be easily accomplished by persons skilled in the art are encompassed in the disclosure of the specification and the accompanying claims.

Examples

[0018] The compositions with the formulas as shown in Table 1 below are prepared in accordance with the following procedure:

	Formula 1		Formula 2	
Epoxy	EPON 828	30	ERL-4221	20
	-	-	EPON1510	10
Curing agent	MHHPA	30	MHHPA	30
Promoter	Quaternary ammonium salt	0.3	Quaternary ammonium salt	0.3

[0019] The epoxy resin, curing agent and promoter are mixed at the predetermined ratios. The resultant mixture is poured into an aluminum container and baked at 120°C for one hour. The thickness of the samples is controlled at about 1 mm. The samples are tested by UV spectrometer for the light transmission rates at the visible range of 400 ~ 800 nm (background: air). The results of the test are shown in the following Table 2.

[0020] The epoxy resin, curing agent and promoter are mixed at the predetermined ratios. The resultant mixture is spin coated onto a silicon wafer. The thickness of the coating is about 5 µm. After being cured by backing, refractive index of the coating is determined by METRICON Model 2010 Prism Coupler at the wavelength of 1320 nm. The results of

the test are shown in the following Table 2.

[0021] The epoxy resin, curing agent and promoter are mixed at the predetermined ratios. The resultant mixture is poured into an aluminum container and baked at 120°C for one hour. The thickness of the samples is controlled at about 1 mm. The samples were tested by pencil-hardness meter for scratch resistance. Moreover, the samples were further molded and tested by thermal mechanical analyzer (PE DMA7.0) to determine their glass transition temperatures. The results of the tests are shown in Table 2 below.

Table 2 : Results of the Tests

	Formula 1	Formula 2
Light transmission	> 90%	> 90%
Refractive index	1.5342	1.4889
Glass transition temperature, °C	125	153
Pencil hardness	2H	3H

[0022] It can be concluded from the results in Table 2 that the material compositions comprising an aliphatic epoxy resin or cycloaliphatic epoxy resin admixed with a curing agent at the ratio of 0.7 to 1.1 possess good light transmission rates, low refractive indices, high glass transition temperatures, and good scratch resistance.

Claims

What is claimed is:

1. A material composition for packaging comprising (a) an epoxy resin and (b) a curing agent, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.7 to 1.1.
2. The composition of claim 1, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.85 to 1.0.
3. The composition of claim 1, wherein said epoxy resin is selected from the group consisting of bisphenol A epoxy resin, bisphenol F epoxy resin, an aliphatic epoxy resin, and a cycloaliphatic epoxy resin and a mixture thereof.
4. The composition of claim 1, wherein said epoxy resin is an aliphatic epoxy resin or a cycloaliphatic epoxy resin or a mixture thereof.
5. The composition of claim 1, wherein said curing agent is an acid anhydride.
6. The composition of claim 5, wherein said acid anhydride is selected from the group consisting of hexahydrophthalic anhydride, methyl hexahydrophthalic anhydride, methyl-bicyclo[2,2,1]-heptene-2,3-dicarboxylic anhydride, succinic anhydride, and hexafluoroisopropylidene-2,2-bisphthalic anhydride, and a mixture thereof.
7. The composition of claim 1, further comprising a promoter.

8. The composition of claim 7, wherein said promoter is selected from the quaternary ammonium salts, imidazole compounds, and salts of 1,8-diazabicyclo[5,4,0]-undec-7-ene, and a mixture thereof.
9. A method for packaging light-sensitive components comprising applying the material composition according to any one of Claims 1 to 8 to the light-sensitive components on a substrate.
10. The method of claim 9, wherein said light-sensitive components are image sensors.
11. The method of Claim 9, wherein said substrate is a printed circuit board or lead frame.
12. A material composition for packaging an image sensor comprising (a) an epoxy resin selected from the group consisting of an aliphatic epoxy resin and a cycloaliphatic epoxy resin and a mixture thereof (b) a curing agent selected from acid anhydrides, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.7 to 1.1.
13. The composition of claim 12, wherein the mixing ratio of said epoxy resin to said curing agent is in the range of from 0.85 to 1.0.
14. The composition of claim 12, wherein said acid anhydride is selected from the group consisting of hexahydrophthalic anhydride, methyl hexahydrophthalic anhydride, methyl-bicyclo[2,2,1]-heptene-2,3-dicarboxylic anhydride, succinic anhydride, and hexafluoroisopropylidene-2,2-bisphthalic anhydride, and a mixture thereof.

15. The composition of claim 12, further comprising a promoter.
16. The composition of claim 15, wherein said promoter is selected from the quaternary ammonium salts, imidazole compounds, and salts of 1,8-diazabicyclo[5,4,0]-undec-7-ene, and a mixture thereof.